

DERWENT ABSTRACT FOR: **JP 04-028740** (Mitsubishi), published 31 Jan1992:

L1 ANSWER 2 OF 9 WPINDEX COPYRIGHT 2001 DERWENT INFORMATION LTD

ACCESSION NUMBER: 1992-085307 [11] WPINDEX

DOC. NO. CPI C1992-039257

TITLE: Prepn. of thermoplastic resin compsn. - prepd. by blending phenylene ether resin etc. with specified polymers and then with olefin resin.

DERWENT CLASS: A17 A17 A25

PATENT ASSIGNEE(S): (MITF) MITSUBISHI PETROCHEMICAL CO LTD; (TCYT) TOYOTA JIDOSHA KK

COUNTRY COUNT 1

PATENT INFORMATION:

PATENT NO	KIND	DATE	WEEK	LA	PG
JP 04028740	A	19920131	(199211)*	14	<--

APPLICATION DETAILS:

PATENT NO	KIND	APPLICATION	DATE
JP 04028740	A	JP 1990-133750	19900525

PRIORITY APPLN. INFO: JP 1990-133750 19900525

AN 1992-085307 [11] WPINDEX

AB JP 04028740 A UPAB: 19931006

The resin compsn. comprises (A), (B), (C) and (D) and is prepd. by blending component (B) or a mixt. of component (B) and at least one kind of component (C) or (D) to obtain compsn. (I) in the 1st step, and then blending compsn. (I) with component (A) and the remaining components in the 2nd step. In the method component (A) = polyolefin resin, 30-78 wt.%, component (B) = polyphenylene-ether resin, 20-68 wt.%, component (C) = a polymer having both alkenyl aromatic cpd. polymer chain (C1) and aliphatic hydrocarbon polymer chain (C2) in one molecule and dynamic shearing modulus at 23 deg.C of 3×10^8 dyne/cm² or higher, 2-50 wt.%, component (D) is rubberlike polymer having dynamic shearing modulus at 23 deg.C of 2×10^8 dyne/cm² or higher : 1-50 pts.wt. per 100 pts.wt. of (A), (B) plus (C).

(A) is pref. isotactic polypropylene. (C) is pref. partially hydrogenated alkenyl cpd.-conjugated diene block copolymer such as hydrogenated styrene-butadiene triblock copolymer. (D) is pref. maleic anhydride grafted propylene-ethylene random copolymer or maleic anhydride grafted 1-butene-ethylene random copolymer.

USE/ADVANTAGE - Process gives a resin compsn. having good mechanical properties, esp. a good balance between falling wt. impact strength and rigidity.

C/O